

NOVA Master Finish

Universal Gypsum Skim & Finish Coat



NOVA Master Finish

Universal Gypsum Skim & Finish Coat

NOVA Master Finish is a gypsum finish plaster that provides a smooth, inert and high-quality surface to internal walls and ceilings, as well as a durable base for applying decorative finishes.

PRODUCT DESCRIPTION

Product: A retarded hemihydrate gypsum-based finishing plaster supplied as a pre-mixed dry powder in a controlled factory environment.

COMPOSITION	Gypsum, selected fillers, polymers
COLOUR	White to off-white, free flowing powder
PACKAGING	25 kg Bag
FEATURES & BENEFITS	• Easy to mix and apply • Provides a smooth, durable matt finish • Suitable for low, medium and medium-high suction backgrounds • Delivers a smooth, high-quality finish to internal walls and ceilings • Supports consistent finishing performance across larger areas • Suitable as a durable base for decorative finishes
USES	• Finishing coat over plasterboards • Application over flat concrete and cement/gypsum undercoat plasters • Internal wall and ceiling finishing

TECHNICAL ANALYSIS

PARAMETERS	SPECIFICATIONS
Wall application thickness	2 mm
Ceiling application thickness	2 mm
Working time	Max. 40 minutes
Set time	Min. 100 minutes
Water required	11.5 to 12.0 litres per 25 kg bag
Coverage	10 m ² / 25 kg bag at 2 mm
Reaction to fire	Class A1
Bond strength	≥ 0.3 MPa
Shelf life	12 months (if stored correctly)

COMPLIANCE and QUALITY

CE marked

Conforms to EN 13279-1:2008, Type B1/20/2

AVCP System 4

Manufactured under an ISO 9001:2015 certified quality management system

For performance details, refer to the Declaration of Performance (DoP)

GUIDANCE FOR USE

SUITABLE SUBSTRATES	- To finish low suction backgrounds such as plasterboard, flat concrete, and other flat surfaces treated with bonding agents. - Also suitable for medium-high suction gypsum or cement-based undercoat plasters
SUBSTRATE PREPARATION	- The background must be clean, dry, and free from dust, oil, and loose material - Ensure all boards are fixed in accordance with the manufacturer's guidelines Plasterboards - Apply only on the face side (non-tapered edges without paper overlap) - Reinforce all joints with Joint Tape - Pre-fill wider gaps (> 3 mm) before reinforcing Gypsum Undercoat Plasters - Surface must be reasonably flat with a good scratch key - Apply finish when the undercoat is set but not fully dry Cement-based Undercoats - Must be completely dried to avoid shrinkage cracks - Provide a stronger scratch key than gypsum undercoats - Allow longer drying times, as shrinkage may appear over days or weeks Concrete Surfaces - Low-suction backgrounds must be pre-treated with suitable bonding agents
MIXING INSTRUCTIONS	- Gradually add NOVA Master Finish to 11.5–12 litres of clean water per 25 kg bag using clean mixing equipment - Mix by hand or with a mechanical mixer at slow speed and high torque - Mix until lumps disperse—avoid over-mixing, as this may reduce workability and strength
APPLICATION	Coat 1 – Base Layer - Apply first coat firmly to spread evenly - Level the surface using consistent trowel pressure - Allow the plaster to stiffen slightly before applying the second coat Coat 2 – Finishing Layer - Apply a thin second coat to achieve a total thickness of 2 mm - Begin trowelling as plaster starts to firm up - Achieve a smooth matt finish by repeated trowelling with clean water as needed
STORAGE	The product should be stored in a cool, dry place and should be used within 12 months of the date of manufacture
USAGE PRECAUTIONS	- Do not apply on frozen surfaces - Protect freshly applied plaster from rapid drying in hot or windy conditions - Do not expose the set plaster to temperatures above 49°C - Ensure proper substrate compatibility before application - Keep out of reach of children

STORAGE INSTRUCTIONS

- Store in a cool, dry, well-ventilated place away from heat sources or direct sunlight
 - Keep away from water and damp areas
 - Avoid using partially used material. Open bags containing partially used material should be kept in a bag with its mouth tightly closed with string to prevent lump formation
 - As temperature, humidity, water addition, and other parameters vary from site to site; the above information should be treated as general guidelines
-

HANDLING

- Walplast complies with its obligations as a supplier of building materials and systems, as required under Section 6 of the Health and Safety at Work etc. Act 1974
 - To reduce the risk of injury from lifting and carrying, manual handling should be carried out safely
 - Employers and workers must follow the Manual Handling Operations Regulations 1992 (MHOR) and HSE guidance (INDG143)
 - Everyone should work together to prevent injuries and ensure a safe workplace
 - For health, safety, and handling guidance, refer to the Safety Data Sheet (SDS)
-

DISPOSAL

- Segregate plaster from non-gypsum waste for recycling where possible, and dispose of in accordance with local authority requirements
-



MASTER FINISH Universal Gypsum Skim & Finish Coat

SUITABLE FOR



Internal walls & ceilings



Concrete backgrounds



Plasterboard



Gypsum or cement undercoat plasters

HOW TO APPLY

Preparation
Ensure background is clean, dry, structurally sound, and free from dust, grease, oil, and loose material. Boards and plastered masonry must be properly fixed and stable.

Mixing
Gradually add NOVA Master Finish to 11.5 - 12 litres of clean water per 25 kg bag using clean mixing equipment. Mix until smooth and lump-free. Avoid over-mixing.

Application
Coat 1 - Base Layer: Apply the 1st coat of approximately 1 mm evenly and level the surface. Allow the plaster to stiffen slightly before applying the 2nd coat.
Coat 2 - Finishing Layer: Apply a thin 2nd coat of approximately 1 mm, once the 1st coat has reached its initial set & feels firm to touch. Ensure an overall thickness of approximately 2 mm.
Note: See TDS for further information.

FEATURES



MIXING
11.5 - 12 litres of clean water per 25 kg bag



THICKNESS
2 mm (Wall/Ceiling application)



COVERAGE
10 m² / 25 kg at 2 mm thickness (coverage may vary depending on surface)



SHELF LIFE
12 months from date of manufacturing in unopened conditions



FINISHING TIME
~100 minutes



COATS
Apply 2 coats by hand

CE
26

Walplast Products Pvt. Ltd.
ISO 9001: 2015 Certified Company

Registered Office: Plot No. A-246, Cross Rd Number 18, T.T.C. Industrial Area, MIDC Industrial Area, Mahape, Navi Mumbai, Maharashtra 400710, INDIA.

Manufacturing Facility: Ankleshwar, Gujarat-393001, INDIA.

Authorised Representative (EU): 24hour Solutions B.V., trading as 24hour-AR, Van Nelloweg 1, 3044 BC Rotterdam, The Netherlands.

DoP No: DoP-NOVA Master Finish-EN-2026-01
DoP No: DoP-NOVA Master Finish-UK-2026-01
EN 13279-1:2008 (Type B1)
 NOVA Master Finish – Universal Gypsum Skim & Finish Coat
 Internal skim and finishing plaster
 Reaction to fire: Class A1
 Thermal resistance: NPd
 Direct airborne sound insulation: NPd
 Country of Origin: India
 Commodity: NOVA MASTER FINISH
 Net Weight: 25 kg

For further information or complaints, please contact
 @ www.walplast.com @ customercare@walplast.com
 ☎ 1800 3000 6650.

FOLLOW US ON    

HEALTH, SAFETY, AND HANDLING INFORMATION



Wear dust mask, eye protection, gloves and helmet. Keep out of reach of children.

- Avoid breathing dust; use well-ventilated areas and suitable PPE where required.
- Dust may cause temporary irritation to eyes, skin, or respiratory system.
- In case of eye contact: rinse with clean water for several minutes; seek medical advice if irritation persists.
- In case of skin contact: wash with soap and water after handling.
- If inhaled: move out for fresh air.
- If swallowed: rinse mouth and seek medical advice if discomfort occurs.
- Store in a cool, dry place and protect from moisture; keep bags sealed and reseal part-used bags.
- Do not apply to frozen substrates and ensure surface suitability before application.
- Protect freshly applied plaster from rapid drying caused by hot or windy conditions.
- Manual handling: use safe lifting techniques. Bag weight 25 kg.
- Dispose of contents and packaging per local authority regulations.

Note: See SDS for health, safety & handling information.

Scan the relevant QR code to access DoP, TDS & SDS.

For EU



For GB





USE NO HOOK

Disclaimer: Technical information is based on knowledge and experience to provide accurate results. These results refer to the long-term application of the product in practice. Recommendations and suggestions are listed for guidance only. As site conditions and application practices are beyond the manufacturer's control, it is the responsibility of the end user to ensure the product's suitability and that they refer to the latest version of this document.